



## BEMAC LABORATORIES

A Subsidiary of Mahaffey Associates Pty Ltd ABN 90 001 629 036  
4 Mary Parade Rydalmere NSW 2116  
PO Box 349 Rydalmere BC NSW 1701  
Phone: (02) 9684 2422 Fax: (02) 9684 2310  
Email: bemac@mahaffey.com.au

This document is issued in accordance  
with NATA's accreditation requirements.  
credited for compliance with ISO/IEC 17025  
Accreditation No. 1393



**Test:** Compressive Strength Testing Of Mortar Cubes  
**Method:** Based on AS1012.9  
**Client :** Timbercrete  
**Job Number :** 8264  
**Material:** Mortar

**Manufacturing Date:** 1-Apr-07  
**Test Date:** 7-May-07  
**Sample Conditioning:** Nil  
**Capping:** Masonite Full Face  
**Sampled by:** Client

Specimen ID	Dimensions (mm)			Load (kN)	Compressive Strength (MPa)
	W	L	H		
1	103.7	96.8	90	30.2	3.0
2	102.6	94.1	90	25.9	2.7
3	103.7	96.0	90	26.9	2.7
				<b>SD</b>	0.0
				<b>Mean</b>	0.0

**Note 1:** Actual Dimensions used

**Note 2:** This Document shall not be reproduced except in full

David Wilmshurst  
Approved Signatory  
10/05/2007